



---

# ARDEX D5

## Ready Mixed Wall Tile Adhesive


---

Extended open time allows a larger area of adhesive to be spread before skinning occurs

Smooth consistency that is easy to work and trowel

White - Suitable for use with translucent tiles

Accommodates limited building movement



---

**ARDEX Australia Pty Ltd**  
20 Powers Road  
Seven Hills NSW 2147  
Phone: 1300 788 780  
Fax: 1300 780 102  
Email: [technicalservices@ardexaustralia.com](mailto:technicalservices@ardexaustralia.com)  
[www.ardexaustralia.com](http://www.ardexaustralia.com)

**ARDEX New Zealand Ltd**  
32 Lane Street  
Woolston, Christchurch 8241  
Phone: 0800 227 339  
Fax: (03) 3849779  
Email: [info@ardexnz.com](mailto:info@ardexnz.com)  
[www.ardex.co.nz](http://www.ardex.co.nz)

# ARDEX D5

## Ready Mixed Wall Tile Adhesive

### DESCRIPTION

ARDEX D5 is a white, ready mixed, thin bed, interior wall tile adhesive. Being a smooth, viscous paste, ARDEX D5 is easy to trowel. It can be used to fix a range of tiles including ceramic tiles, non moisture sensitive natural stones, mosaics and translucent tiles in kitchens, bathrooms and laundries.

ARDEX D5 meets ISO 13007 requirements for a D1 TE adhesive – normal dispersion adhesive with extended open time, and is suitable for use in residential or commercial situations.

### FOR FIXING (TILE TYPES)

All ceramic wall tiles including monocottura, natural stones (excluding moisture sensitive) and glass mosaics.

### TO (SUBSTRATES)

Concrete, cement renders, fibre-cement sheet, plasterboard. ARDEX/Undertile liquid applied waterproofing membranes (not suitable when using dense tiles over such non absorbent substrates nor for shower hobs due to prolonged drying times)

### SUBSTRATE PREPARATION

The surface being adhered to must be clean, firm and free of dust, dirt, oil, grease, curing compounds, release agents and other barrier materials, as well as being strong enough to support the weight of the tiles being fixed. Ensure surfaces are dry before tiling, with no residue or permanent damp.

Ensure that the substrate's required drying time, as given in the relevant part of AS 3958, is allowed to elapse prior to fixing the tiles. Prime porous substrates with ARDEX Multiprime.

### Concrete

This includes precast, in-situ and wood floated concrete. Any surface laitance, concrete sealers, curing compounds, and other materials should be removed from the surface prior to tiling. The surface should be true, level and have adequate surface profile to provide a mechanical key. Smooth surfaces and/or dense concrete greater than 35MPa must be mechanically roughened prior to tiling.

### Cement Render/Screeds

New renders should be finished with a wood float to the required surface regularity and be allowed to cure for at least 7 days.

### Plasterboard on Walls

Provided that these boards are firmly and rigidly fixed to adequately support the tile bed, tiles can be fixed directly with no need to prime the cardboard surface. Where sheets are jointed, ARDEX Multiprime must be used over the base jointing compound. Do not use the topping compound in areas which are to be tiled.

### Fibre-Cement Sheet on Walls

Remove surface dust with a damp sponge or prime with ARDEX Multiprime prior to tiling.

### Painted Surfaces

Thoroughly remove painted surfaces mechanically, do not use paint stripper or solvents. Allow surface to dry after cleaning.

### MIXING

Premixed, no mixing required.

### FIXING TECHNIQUE

Before fixing ensure the substrate has been prepared and the tiles are free from dust. Tiles should be fixed in accordance with AS 3958.

Substrate surface, type and size of the tiles will determine the selection of the trowel. As a general guide use a 6 x 6 x 6mm notched trowel for walls. ARDEX D5 can be applied at a bed thickness greater than 1.5mm or less than 3mm. The tiles must be pressed firmly into the freshly combed mortar bed to ensure good contact with the adhesive. Slide the tile at right angles to the notch pattern to ensure 100% coverage on the back of the tile. Lift a tile from time to time to check that there are no voids beneath the tile. Do not spot fix. Any surplus adhesive must be removed from the surface of the tile and joints, before the adhesive sets.

ARDEX D5 has an open time of 40 minutes and an adjustment time of 60 minutes. Please be aware of site conditions when considering these times and only spread enough adhesive so that the tiles can be fixed while the mortar is still wet. All tools should be cleaned with water immediately after use.

### MOVEMENT JOINTS

Movement joints must be in accordance with AS 3958. As a general guide for walls, incorporate movement joints at internal corners, fixtures interrupting the tile surface and at 3-4.5 metre intervals.

### GROUTING

Grouting can proceed once the tile bed has hardened sufficiently so that tiles will not be dislodged. Typically the tile bed is hard enough after approximately 24 hours at 23°C and 50% relative humidity. Allow longer for dense tiles/substrates, humid climates and low temperatures.

The tile joints should be grouted with the appropriate ARDEX grout.

### COVERAGE

20kg of ARDEX D5 is sufficient for approximately 11m<sup>2</sup> on walls. The coverage will vary depending on substrate condition, tile type and application technique.

### PACKAGING

ARDEX D5 is packed in plastic pails – net weight 20kg.

### SHELF LIFE

ARDEX D5 has a shelf life of 12 months when stored in the original unopened packaging, in a dry place at 23°C and 50% relative humidity. Do not store below 5°C.

### Pay attention to the following:

When large format or dense tiles are being used do not use ARDEX D5 over non-absorbent substrates such as waterproofing membranes or shower hobs due to prolonged drying times. ARDEX D5 is not suitable for continuous immersion applications, such as swimming pools and water tanks. ARDEX provides other systems.

For setting of moisture sensitive natural stones, please refer to products in the ARDEX Natural Stone System.

### SAFETY PRECAUTIONS

This product is classified as non-hazardous according to WorkSafe Australia criteria. Avoid contact with skin and eyes; in case of contact with the eyes, rinse immediately with plenty of water and seek medical advice; wear suitable gloves and eye protection and keep the product out of the reach of children. Avoid inhalation of vapours.

For further material safety data, consult the latest Material Safety Data Sheet.

### TECHNICAL DATA

**Colour:** White paste  
**pH:** Approx 8.5 – 9.5

### Application Properties at 23°C and 50% RH

**Open Time:** 40 minutes  
**Adjustment Time:** 60 minutes  
**Grouting Time:** 24 hours

### Mechanical Properties (ISO 13007)

**Shear adhesion strength:** 1.0 - 2.0 MPa  
**Classification:** D1 TE

### Toll Free Technical Services: 1800 224 070 (Australia) 0800 227 339 (NZ)

### ARDEX Australia Pty Ltd

20 Powers Road  
Seven Hills NSW 2147  
Phone: 1300 788 780  
Fax: 1300 780 102  
Email: [technicalservices@ardexaustralia.com](mailto:technicalservices@ardexaustralia.com)  
[www.ardexaustralia.com](http://www.ardexaustralia.com)

### ARDEX New Zealand Ltd

32 Lane Street  
Woolston, Christchurch 8241  
Phone: 0800 227 339  
Fax: (03) 3849779  
Email: [info@ardexnz.com](mailto:info@ardexnz.com)  
[www.ardex.co.nz](http://www.ardex.co.nz)

### DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standard, our instructions and recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them. © ARDEX Australia Pty Ltd 2015. All aforementioned products are the trade marks of ARDEX Australia Pty Ltd, its licensors and affiliates.